



COVESTRO DEUTSCHLAND AG [PC RESINS]

Chempark
Gebäude B207
Leverkusen, 51368 Germany



Makrolon: 6165 X + (z)(f1), 6165 X + RE (f1)

Polycarbonate (PC), pellets, flame retardant

- (f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C.
- (z) - Material designation and color code may be followed by up to three letters and/or three numbers (does not include grades which are separately recognized with above material designation and suffix)
- + - Material designations may be followed by a six digit numerical code denoting color.

可燃性	值	测试方法
UL 阻燃等级		UL 94
1.2 mm, ALL	V-0	IEC 60695-11-10, -20
1.5 mm, ALL	V-0	
3.0 mm, ALL	V-0	
灼热丝易燃指数		IEC 60695-2-12
1.2 mm	960 °C	
1.5 mm	960 °C	
3.0 mm	960 °C	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
1.2 mm	PLC 3	
1.5 mm	PLC 3	
3.0 mm	PLC 1	
高电弧燃烧指数(HAI)		UL 746A
1.2 mm	PLC 3	
1.5 mm	PLC 2	
3.0 mm	PLC 2	
相比耐漏电起痕指数(CTI)	PLC 3	UL 746A
高电压电弧起痕速率 (HVTR)	PLC 4	UL 746A
体积电阻率	1.0E+16 ohms-cm	ASTM D257 IEC 60093
耐电弧性	PLC 5	ASTM D495
热性能	值	测试方法
RTI Elec		UL 746B
1.2 mm	125 °C	
1.5 mm	125 °C	
3.0 mm	125 °C	
RTI Imp		UL 746B
1.2 mm	115 °C	
1.5 mm	115 °C	
3.0 mm	115 °C	
RTI		UL 746B
1.2 mm	125 °C	
1.5 mm	125 °C	
3.0 mm	125 °C	



物理性能	值	测试方法
室外适用性	f1	UL 746C