



COVESTRO DEUTSCHLAND AG [PC RESINS]

Chempark
Gebäude B207
Leverkusen, 51368 Germany



Makrolon: FR7087 + (z)

Polycarbonate (PC), pellets, flame retardant

- (z) - Material designation and color code may be followed by up to three letters and/or three numbers (does not include grades which are separately recognized with above material designation and suffix)
- + - Material designations may be followed by a six digit numerical code denoting color.

可燃性	值	测试方法
UL 阻燃等级		UL 94
1.5 mm, ALL	V-2	IEC 60695-11-10, -20
2.2 mm, ALL	V-0	
3.0 mm, ALL	V-0, 5VA	
灼热丝易燃指数		IEC 60695-2-12
1.5 mm	960 °C	
2.2 mm	960 °C	
3.0 mm	960 °C	
热灯丝点火温度		IEC 60695-2-13
1.5 mm	930 °C	
2.2 mm	930 °C	
3.0 mm	960 °C	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
1.5 mm	PLC 2	
2.2 mm	PLC 1	
3.0 mm	PLC 1	
高电弧燃烧指数(HAI)		UL 746A
1.5 mm	PLC 4	
2.2 mm	PLC 3	
3.0 mm	PLC 3	
相比耐漏电起痕指数(CTI)	PLC 3	UL 746A
高电压电弧起痕速率 (HVTR)	PLC 2	UL 746A
热性能	值	测试方法
RTI Elec		UL 746B
0.75 mm	125 °C	
1.5 mm	125 °C	
2.2 mm	125 °C	
3.0 mm	125 °C	
RTI Imp		UL 746B
0.75 mm	80.0 °C	
1.5 mm	80.0 °C	
2.2 mm	80.0 °C	
3.0 mm	80.0 °C	



热性能	值	测试方法
RTI		UL 746B
0.75 mm	80.0 °C	
1.5 mm	85.0 °C	
2.2 mm	85.0 °C	
3.0 mm	85.0 °C	