

ACRYLITE® Satinice df21 8N

Product Profile:

ACRYLITE® Satinice df21 8N, based on ACRYLITE® 8N, is characterized by diffuse scattering of light.

Typical properties of ACRYLITE® molding compound are

- good melt flow rate
- high mechanical strength, surface hardness and mar resistance
- very good weather resistance.

Special properties of ACRYLITE® Satinice df21 8N are

- good lightdiffusion combined with excellent light transmission.

Application:

Used for injection molding items for lighting engineering applications

Examples:

displays, backlight units

Processing:

ACRYLITE® Satinice df21 8N can be processed on injection molding machines with 3-zone general purpose screws for engineering thermoplastics.

Packaging:

ACRYLITE® Satinice df molding compounds are supplied as pellets of uniform size, packaged in 25kg polyethylene bags; other packaging on request.

Properties:

	Parameter	Unit	ASTM-Standard	ACRYLITE® Satinice df21 8N
Mechanical Properties				Typical Value
Tensile Strength		psi [MPa]	D 638	11500 [79.3]
Tensile Modulus		x10 ⁶ psi [GPa]	D 638	0.55 [3.8]
Tensile Elongation @ Yield		%	D 638	4
Tensile Elongation @ Break		%	D 638	4
Flexural Strength		psi [MPa]	D 790	20000 [138]
Flexural Modulus		x10 ⁶ psi [GPa]	D 790	0.5 [3.5]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.3 [16]
Rockwell Hardness		M Scale	D 785	95
Thermal Properties				
Vicat Softening Point	264 psi	°F [°C]	D 1525	246 [119]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	221 [105]
Coeff. of Linear Therm. Expansion	32 - 312°F	in/ in/°F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 - 100°C	mm/mm/°C	D 696	0.000072
Rheological Properties				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	3.1
Optical Properties				d = 3.2 mm
Light Transmittance		%	D 1003	90
Haze		%	D 1003	83
Yellowness Index			E 313	<2
Other Properties				
Specific Gravity			D 792	1.19
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.003 - 0.006
Bulk Density		g/cc	D 1895	0.66

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Roehm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved.

Roehm America LLC • 299 Jefferson Road • Parsippany NJ 07054
www.acrylite-polymers.com
www.roehm.com

Ref. No.: F261-26 A1142-A Date: 07/16/2020