

 $\underline{\mathsf{Home}} > \underline{\mathsf{Product}\,\mathsf{Introduction}} > \underline{\mathsf{Catalogues}} > \underline{\mathsf{DURAFIDE} \mathsf{@PPS}} > \mathsf{0220A9}\,\mathsf{HD9100}$

0220A9 HD9100 (ISO)

HELP



Recommended browser is Internet Explorer 8 or higher.

0220A9.pdf (168KB)

Search by grade name(OR)

To move to other brands

I tem	Unit	Test Method	Unfilled
			0220A9
			High toughness
Color No.			HD9100
		ISO11469 (JIS K6999)	>PPS<
Density	g/ cm³	ISO 1183	1.35
Water absorption (23°C, 24hrs, 1mmt)	%	ISO 62	0.04
Melt viscosity (310°C,1000/sec)	Pa·s	ISO 11443	500
Tensile strength	MPa	ISO 527-1,2	90
Strain at break	%	ISO 527-1,2	15 *1
Flexural strength	MPa	ISO 178	140
Flexural modulus	MPa	ISO 178	3,800
Charpy notched impact strength (23°C)	kJ/m²	ISO 179/1eA	3.3
Temperature of deflection under load (1.8MPa)	°C	ISO 75-1,2	100
Coefficient of linear thermal expansion (Normal temperature, Flow direction)	x10 ⁻⁵ /°C	Our standard	4
Coefficient of linear thermal expansion (Normal temperature, Transverse direction)	x10 ⁻⁵ /°C	Our standard	6
Electric strength (3mmt)	kV/mm	IEC 60243-1	19
Volume resistivity	Ω·cm	IEC 60093	2 x 10 ¹⁶
Volume resistivity (Our standard)	Ω·cm		-
Relative permittivity (1kHz)		IEC 60250	3.6
Relative permittivity (1MHz)		IEC 60250	3.6
Dielectric dissipation factor (1kHz)		IEC 60250	0.001
Dielectric dissipation factor (1MHz)		IEC 60250	0.001
Relative permittivity (2GHz)		Cavity resonator method	
Dielectric dissipation factor (2GH z)		Cavity resonator method	-
Tracking resistance (CTI)	V	IEC 60112	125
Arc resistance	S	ASTM D495	115
Rockwell hardness	M(Scale)	ISO2039-2	95
Flammability		UL94	V-0
The yellow card File No.			E109088
Appropriate List number of Ministerial Ordinance for Export Trade Control			Item 16 of Appendix

If item's description doesn't include test condition, the item is examined at 23 deg. C. (RT)

*1) Nominal strain at break

1 of 2 12/19/2016 10:57 AM

Data of detailed properties

Moldability	Flowability	To view the data
Moldability	Mold Shrinkage	To view the data
Moldability	After-shrinkage	To view the data
Moldability	Residence in Cylinder	To view the data
Short-term mechanical properties	Tensile properties	To view the data
Short-term mechanical properties	Flexural Properties	To view the data
Short-term mechanical properties	Effect of Temperature on Maximum Stress	To view the data
Short-term mechanical properties	Effect of Temperature on Modulus	To view the data
Long-term mechanical properties	Fatigue Properties	To view the data
Endurance	Chemical Resistance, Hot Water Resistance, Heat and Moisture Resistance	To view the data
Thermal properties	Coefficient of Linear Thermal Expansion	To view the data

All figures in the table are the typical values of the material and not the minimum values of the material specifications.

All data shown here are not always applicable to parts used under different conditions. We do not guarantee that these data are directly applicable to the application conditions of users and we ask each user to make his own decision on the application.

For safe handling of materials we supply, it is advised to refer to the Material Safety Data Sheet "SDS" of the proper material.

This brochure is edited based on reference literatures, information and data currently available to us. So the contents of this brochure are subject to change without notice due to new data.

Site Map

Privacy policy

Registered Trademarks

Website Privacy Policy

Precautions



Copyright 2001-2016 Polyplastics Co., Ltd. All rights reserved.