



EASTMAN CHEMICAL CO PERFORMANCE PLASTICS
PO BOX 1969
KINGSPORT, TN 37662-1963 United States



TRITAN: TX1001, Renew TX1001-25, Renew TX1001-50

Co-Polyester, pellets

NOTE - May be followed by A, C, E or G.

可燃性	值	测试方法
UL 阻燃等级		
1.6 mm, ALL	HB	UL 94
2.5 mm, ALL	HB	UL 94
3.2 mm, ALL	HB	UL 94
3.2 mm, ALL	HB40	IEC 60695-11-10, -20
1.6 mm, ALL	HB75	IEC 60695-11-10, -20
2.5 mm, ALL	HB75	IEC 60695-11-10, -20
灼热丝易燃指数		IEC 60695-2-12
1.6 mm	850 °C	
2.5 mm	800 °C	
热灯丝点火温度		IEC 60695-2-13
1.6 mm	675 °C	
2.5 mm	675 °C	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
1.6 mm	PLC 4	
2.5 mm	PLC 4	
3.2 mm	PLC 0	
热性能	值	测试方法
RTI Elec		UL 746B
1.6 mm	95.0 °C	
2.5 mm	95.0 °C	
3.2 mm	95.0 °C	
RTI Imp		UL 746B
1.6 mm	95.0 °C	
2.5 mm	95.0 °C	
3.2 mm	95.0 °C	
RTI		UL 746B
1.6 mm	95.0 °C	
2.5 mm	95.0 °C	
3.2 mm	95.0 °C	