

HOSTAFORM® S 9363 XAP®2

Impact modified, improved modulus and weld line, low emission

Hostaform® acetal copolymer grade S 9363 XAP®2 is an impact modified grade for demanding applications. Hostaform® S 9363 XAP®2 provides good impact strength while improving modulus and weld line strength over standard impact modified grades such as Hostaform® S 9063, and also exhibits exceptional low emission performance meeting or exceeding the requirements of many automotive markets. Chemical abbreviation according to ISO 1043-1: POM-HI

Rheological properties

Melt volume-flow rate	5.5 cm ³ /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	
Moulding shrinkage, parallel	1.8 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.6 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	2000 MPa	ISO 527-1/-2
Yield stress, 50mm/min	50 MPa	ISO 527-1/-2
Yield strain, 50mm/min	12 %	ISO 527-1/-2
Flexural Modulus	2000 MPa	ISO 178
Charpy impact strength, 23°C	NB kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	NB kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	13 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	8 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	13 kJ/m ²	ISO 180/1A
Izod notched impact strength, -40°C	8 kJ/m ²	ISO 180/1A
Hardness, Rockwell, M-scale	65	ISO 2039-2

Thermal properties

Melting temperature, 10°C/min	166 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	84 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	148 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 10N	161 °C	ISO 306
Coeff. of linear therm. expansion, parallel	110 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	110 E-6/K	ISO 11359-1/-2

Other properties

Humidity absorption, 2mm	0.25 %	Sim. to ISO 62
Water absorption, 2mm	0.8 %	Sim. to ISO 62
Density	1380 kg/m ³	ISO 1183

HOSTAFORM® S 9363 XAP® 2

Injection


Drying Temperature	100 - 120 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Max. mould temperature	60 - 70 °C
Back pressure	2 MPa
Injection speed	slow

Characteristics

Additives	Release agent
-----------	---------------


HOSTAFORM® S 9363 XAP®2

Stress-strain




HOSTAFORM® S 9363 XAP®2

Secant modulus-strain



HOSTAFORM® S 9363 XAP® 2

True stress-strain



HOSTAFORM® S 9363 XAP® 2

Processing Texts

Pre-drying

Drying is suggested to help achieve low emission performance and to counter if material has contacted moisture through improper storage and handling.

Other Approvals

Other Approvals

OEM	Specification	Additional Information
Mercedes-Benz Group (Daimler)	DBL 5404	BQF
Ford	WSF-M4D618-A	Natural
Renault	UB15	
SAIC Motor	SMTC 5 310 020	
Li Auto	Q/LiA5310020	2021 (V2)