

LUTENE[®] LB7500

Low Density Polyethylene

Applications

- Flexible package(tie layer or sealant layer of laminating film), Paper and paper board

Description

- LUTENE[®] LB7500 is mainly intended for extrusion coating and can be processed at high speed with uniform thickness and width.
- LUTENE[®] LB7500 has a good adhesion strength with Al-foil, polymer film, paper, paper board and other substrate and excellent neck-in characteristics.
- LUTENE[®] LB7500 contains no additives.
- LUTENE[®] LB7500 complies with U.S. FDA 21CFR 177.1520 C and Japanese Ministry of Health and Welfare Notification N.20 Standard.

Typical properties

Characteristics	Test Method	Unit	Value
Physical⁽¹⁾			
MFR(190°C, 2.16Kg)	ASTM D1238	g/10min	7.2
Density	D792	g/cm ³	0.918
Mechanical⁽²⁾			
Tensile Strength at Yield	D638	Mpa	8.8
Tensile Strength at Break	D638	Mpa	11.3
Elongation at Break	D638	%	>500
Shore hardness(Shore D)	D2240	-	43
Thermal			
Melting Temperature	LG Method	°C	106
Vicat Softening Point	D1525	°C	83
Thermal			
Neck-in (at speed 150m/min)	LG Method	mm	25
Max. Coating Speed (at weight 9g/m ²)	LG Method	m/min	500
Min. Coating Weight (at speed 500m/min)	LG Method	g/m ²	9

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

For additional sales, order and technical assistance

Head office PO Division, LG Chem Ltd.
Yeoui-do P.O.Box 672, 21st floor LG Twin Tower,
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.

TS&D TECH Center. Polyolefin
188, Munji-ro, Yuseong-gu, Daejeon, 34122, Korea.
Tel. 82-42-722-5074

LUTENE[®] LB7500

Low Density Polyethylene

Processing information

- LUTENE[®] **LB7500** can be easily processed on all standard extrusion coating equipment.
- Optimum melt temperature on commercial extrusion coating equipment is range of 280 to 330 °C.

Storage and handling Recommendations

- LUTENE[®] **LB7500** should be stored in a dry and dust free conditions.
- Keep below 45 °C taking away from direct sunlight

For additional sales, order and technical assistance

Head office PO Division, LG Chem Ltd.

Yeoui-do P.O.Box 672, 21st floor LG Twin Tower,
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.

TS&D**TECH Center. Polyolefin**

188, Munji-ro, Yuseong-gu, Daejeon, 34122, Korea.
Tel. 82-42-722-5074