

Technical Data Sheet

Hostalen PP HP1886



Polypropylene, Random Copolymer

Product Description

Hostalen PP HP1886 is a very low flow random copolymer with good stiffness/toughness balance, outstanding creep and stress cracking resistance. Hostalen PP HP1886 features low haze and yellowing resistance in contact with cooling water. Typical customer use is automotive expansion tanks. Hostalen PP HP1886 is not intended for medical and pharmaceutical applications.

Regulatory Status

For regulatory compliance information, see Hostalen PP HP1886 [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand; Europe; North America; South & Central America
Application	Non-fuel Reservoirs; Underhood
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Chemical Resistance; Good Heat Resistance; Good Stiffness; Good Toughness; High Creep Resistance; Low Flow

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/5.0 kg)	1.4	g/10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	1300	MPa	ISO 178
Tensile Modulus, (23 °C)	1400	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C, 50 mm/min)	34	MPa	ISO 527-1, -2
Tensile Strain at Yield, (23 °C, 50 mm/min)	10	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	14	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	No Break		ISO 179
Thermal			
Vicat Softening Temperature, (A50)	151	°C	ISO 306
Heat Deflection Temperature A, (1.80 MPa, Unannealed)	54	°C	ISO 75A-1, -2
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	101	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.