



# The Polyolefin Company (Singapore) Pte. Ltd.

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720

Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293 2748

Plant : 401 Ayer Merbau Road, Singapore 628285

Website: www.tpc.com.sg

Co. Reg. No.: 198001666D

## COSMOPLENE® FL7540L

### CHARACTERISTICS

**COSMOPLENE FL7540L** is Polypropylene Terpolymer product with good Aluminum adhesiveness, good process stability and high gloss.

### APPLICATIONS

**COSMOPLENE FL7540L** is designed for Aluminum metalized cast film (M-CPP) application. **FL7540L** contains antiblocking agent only.

**FL7540L** complies with U.S. FDA Regulation 21 CFR 177.1520 (C) 3.2a, as long as it is used unmodified and processed according to standard manufacturing practices in the industries.

Note : Direct food contact is subjected to the extraction provisions of the regulation on the finished food contact article.

### PHYSICAL PROPERTIES

ITEM	UNIT	FL7540L	TEST METHOD
Melt Flow Rate	g/10 mins	7.0	ASTM D1238
Density	g/cm <sup>3</sup>	0.90	ASTM D792
Tensile Strength at break	MPa	44	ASTM D638
Elongation	%	850	ASTM D638
Stiffness	MPa	980	ASTM D747
Melting Point	°C	138	TPC METHOD

### FILM PROPERTIES (30μ)

ITEM	UNIT	FL7540L	TEST METHOD
Haze	%	2.0	ASTM D1003
Gloss	%	165	ASTM D2457
Young Modulus (MD)	MPa	520	TPC METHOD
TD)		530	
Heat Seal Temperature	°C	125	TPC METHOD
Resin Stock Temperature	°C	240	
Chill Roll Temperature	°C	50	

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/ recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.



Jan 2011

**COSMOPLENE®**

**COSMOTHENE®**

**COSMOTHENE® EVA**

POLYPROPYLENE

LOW DENSITY POLYETHYLENE

ETHYLENE VINYL ACETATE COPOLYMER