

Topilene® R701**Polypropylene Random Copolymer**
For High Clarity Injection Molding**Product Description**

Topilene® R701 is a specially designed polypropylene random copolymer that features excellent transparency and high flowability. It is suitable for food containers, medical syringes, transparent containers and housewares, stationery and TWIM parts. **Topilene® R701** is phthalate-free and it complies with FDA requirements in the code of Federal Regulations in 21 CFR 177.1520 for food contact. This product passed the US Pharmacopoeia test(USP class VI) as well as the European Pharmacopoeia test(EP 3.1.6) and can be used as a medical purpose.

Characteristics

Typical Application	Food containers / Transparent container / Housewares / Medical syringes / Stationery / TWIM(Thin Wall Injection Molding) parts
Features	High transparency / Excellent flowability & Processability / Phthalate-Free / Non Peroxide Cracking / Excellent stiffness and impact strength balance

Typical Properties

Resin Properties	Method	Value	Unit
Melt Index(230°C, 2.16kg)	ASTM D1238	20	g/10min
Density	ASTM D792	0.90	g/cm³
Tensile Strength at Yield	ASTM D638	300	kg/cm²
Flexural Modulus	ASTM D790	11,000	kg/cm²
Notched Izod Impact Strength(23°C)	ASTM D256	6.0	kg-cm/cm
Rockwell Hardness	ASTM D785	90	R-Scale
Heat Deflection Temperature	ASTM D648	90	°C
Haze(2mm)	ISO 14782	20	%

The values listed above are typical values for reference purpose only and shall not be construed as specifications. **Topilene®** is a registered trademark owned or used by HYOSUNG CORPORATION.

Energy Savings

Topilene® R701 provides improved aesthetics at significantly lower process temperatures that leads to lowered energy consumptions, shortened cycle time and improved productivity. It enables an average of 10% energy savings for production of clarified PP parts.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition)

Contacts

Head Office	235, Banpo-daero, Seocho-gu, Seoul, Korea 06578 Tel: +82-2-2146-5451~7 Fax: +82-2-2146-5428
Online	www.hyosungchemical.com www.topilene.com

Milliken
Millad® NX™ 8000
The New Standard In Clear Polypropylene

**HYOSUNG CHEMICAL**