



ABS樹脂

Formosa Chemical & Fibre Corporation

| 項目 | 單位 | 測試方式 | 測試條件 | 深黑色押出級 |
|----------|---|-------------|----------------------|--------|
| 型号 | | | | AE10EP |
| 熔融指數 | g/10 min | ASTM D-1238 | 220°C × 10kg | 5.7 |
| IZOD沖擊強度 | kg-cm/cm | ASTM D-256 | 23 °C, 1/4", Notched | 41 |
| 抗張強度 | kg/cm ² | ASTM D-638 | 23 °C, 50mm/min | 370 |
| 彎曲模數 | kg/cm ² | ASTM D-790 | 23 °C, 15mm/min | 20000 |
| 特性 | MI(220°C×10kg): 5.7 Izod (ASTM,1/4"): 41 FM(ASTM): 20000 TS(ASTM): 370 押出成型用 超高耐衝擊性 高剛性 | | | |

All tests were run under laboratory conditions, ASTM, ISO testing procedures.

The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 FAX: +886-2-27131649

Address: 11470 台北市內湖區南京東路六段380號A2棟



www.fcfc-plastics.com