



ABS樹脂

Formosa Chemical & Fibre Corporation

項目	單位	測試方式	測試條件	20%GF強化規格
型号				AG20GF
熔融指數	g/10 min	ASTM D-1238	220°C × 10kg	15
IZOD沖擊強度	kg-cm/cm	ASTM D-256	23 °C, 1/4", Notched	8.7
抗張強度	kg/cm ²	ASTM D-638	23 °C	1100
彎曲強度	kg/cm ²	ASTM D-790	23 °C	69510
特性	MI(220°C×10kg):15 Izod (ASTM,1/4"):8.7 FM(ASTM):69510 TS(ASTM):1100 尺寸安定性、耐熱性			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 FAX: +886-2-27131649
Address: 11470 台北市內湖區南京東路六段380號A2棟



www.fcfc-plastics.com