

ABS樹脂



Formosa Chemical & Fibre Corporation

項目	單位	測試方式	測試條件	電鍍級
型號				AG22AT
熔融指數	g/10 min	ASTM D-1238	220°C × 10kg	15
IZOD沖擊強度	kg-cm/cm	ASTM D-256	23 °C, 1/4", Notched	25
抗張強度	kg/cm ²	ASTM D-638	23 °C	440
彎曲強度	kg/cm ²	ASTM D-790	23 °C	24000
特性	MI(220°C×10kg):15 Izod (ASTM,1/4"):25 FM(ASTM):24000 TS(ASTM):440 高耐衝擊性、電鍍用			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649
Address: 11470 台北市內湖區南京東路六段380號A2棟



www.fcfc-plastics.com