



ABS樹脂

項目	單位	測試方式	測試條件	電鍍級
型號				AG23AT-M
特性			MI(220°C×10kg):21 Izod (ASTM,1/4"):29 FM(ASTM):23500 TS(ASTM):450 高耐衝擊性 電鍍用	

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 FAX: +886-2-27131649

Address: 11470 台北市內湖區南京東路六段380號A2棟



www.fcfc-plastics.com