FORMOSA CHEMICALS & FIBRE CORP PLASTICS DIV 201 TUNG HWA N RD

TAIPEI, 105 Taiwan

TAIRILOY: AC250(+)

Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS), pellets

(+) - Replace by one digital 0-9 or one alphabet A-Z, unconcerned with formula or constituent changed

Flammability	Value	Test Method
Flame Rating		
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
Electrical	Value	Test Method
Hot-wire Ignition (HWI)		UL 746
1.5 mm	PLC 3	
3.0 mm	PLC 3	
High Amp Arc Ignition (HAI)		UL 746
1.5 mm	PLC 0	
3.0 mm	PLC 0	
Comparative Tracking Index (CTI)	PLC 0	UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 2	UL 746
Arc Resistance	PLC 5	ASTM D495
Thermal	Value	Test Method
RTI Elec		UL 746
1.5 mm	60.0 °C	
3.0 mm	60.0 °C	
RTI Imp		UL 746
1.5 mm	60.0 °C	
3.0 mm	60.0 °C	
RTI Str		UL 746
1.5 mm	60.0 °C	
3.0 mm	60.0 °C	

UL and the UL logo are trademarks of UL LLC Copyright © 2020 All Rights Reserved. | www.ul.com

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 smallscale test data is intended solely for determining the flammability of plastic materials used in the components and parts of endproduct devices and appliances, where the acceptability of the combination is determined by UL.

