

PC/ABS合金(合膠)



Formosa Chemical & Fibre Corporation

项目	单位	测试方式	测试条件	耐燃级
型号				AC3250
熔融指数	g/10 min	ASTM D-1238	240°C × 5kg	25
熔融指数	g/10 min	ASTM D-1238	260°C × 2.16kg	12
IZOD冲击强度	kg-cm/cm	ASTM D-256	23°C, 3.2mm, Notched	6.5
比重	-	ASTM D-792	23°C/23°C	1.3
抗張強度	kg/cm²	ASTM D-638	23 °C	640
弯曲强度	kg/cm²	ASTM D-790	23 °C	1110
弯曲模数	kg/cm²	ASTM D-790	23 °C	41600
洛氏硬度	R-scale	ASTM D-785	23 °C	R-115
卫式软化点	°C	ASTM D-1525	VICAT(10N °C)	103
热变形温度	°C	ASTM D-648	Unannealed 18.6 kg/cm² (1.8Mpa)(6.4mm)	89
收缩率	%	ASTM D-955	3.2mm	0.3 ~ 0.5
燃烧性		UL-94	File No. E162823	v-0 1.2 ~ 3 mm 5VA 3 mm 5VB 2 mm
特性	耐燃，无卤			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.
TEL:+886-2-27122211 FAX: +886-2-27131649
Address: 11470 台北市内湖区南京东路六段380号A2栋



www.fcfc-plastics.com