



# PC/ABS合金(合膠)

Formosa Chemical & Fibre Corporation

项目	单位	测试方式	测试条件	耐燃级
型号				AC3300
熔融指数	g/10 min	ASTM D-1238	240°C × 5kg	42
熔融指数	g/10 min	ASTM D-1238	260°C × 2.16kg	30
IZOD冲击强度	kg-cm/cm	ASTM D-256	23°C, 3.2mm, Notched	29
比重	-	ASTM D-792	23°C/23°C	1.18
抗張強度	kg/cm <sup>2</sup>	ASTM D-638	23 °C	610
弯曲强度	kg/cm <sup>2</sup>	ASTM D-790	23 °C	1030
弯曲模数	kg/cm <sup>2</sup>	ASTM D-790	23 °C	26000
洛氏硬度	R-scale	ASTM D-785	23 °C	R-118
燃烧性		UL-94	File No. E162823	v-0 1.2 ~ 1.8 mm 5VB 1.6 ~ 1.8 mm
特性	耐燃, 无卤			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.  
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 FAX: +886-2-27131649  
Address: 11470 台北市内湖区南京东路六段380号A2栋



[www.fcf-plastics.com](http://www.fcf-plastics.com)