

SABIC® PP PCGH19

PP HOMOPOLYMER

DESCRIPTION

SABIC® PP grades for healthcare applications are produced under controlled conditions resulting in high product quality, consistency and a high level of purity.

SABIC® PP PCGH19 is typically used by our customers for injection molding of healthcare applications such as caps and closures, 3-part syringes and other thin walled parts. This grade offers a high stiffness combined with good flow properties. Due to its narrow molecular weight distribution it is typically used by our customers for thin walled, warpage critical applications.

Compliance to regulations:

SABIC® PP PCGH19 complies with the relevant monographs of the European Pharmacopoeia (EP) and the United States Pharmacopoeia (USPVI). The product mentioned herein may not be used for medical healthcare devices or materials intended for temporary or permanent implementation in the human body.

IMDS 7172624

TYPICAL PROPERTY VALUES

Revision 20230111

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	19	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
FORMULATION			
Anti static agent	□	-	-
Nucleating agent	□	-	-
MECHANICAL PROPERTIES			
Tensile test			
stress at yield	37	MPa	ISO 527-2 1A
strain at yield ⁽¹⁾	9	%	ISO 527-2 1A
tensile modulus ⁽²⁾	1800	MPa	ISO 527-2 1A
Izod impact notched			
at 23 °C	3.0	kJ/m ²	ISO 180/1A
Charpy Impact Strength Notched			
at 23 °C	4.0	kJ/m ²	ISO 179/1eA
Hardness Shore D	71	-	ISO 868
THERMAL PROPERTIES			
Heat deflection temperature ⁽³⁾			
at 0.45 MPa (HDT/B)	90	°C	ISO 75
at 1.80 MPa (HDT/A)	60	°C	ISO 75
Vicat Softening Temperature ⁽⁴⁾			
at 50 N (VST/B)	94	°C	ISO 306
at 10 N (VST/A)	152	°C	ISO 306

- (1) Speed of testing: 50 mm/min
- (2) Speed of testing: 1 mm/min
- (3) Flat wise (testbar 80*10*4mm)
- (4) Temperature rate: 120°C/h

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.