

Solumer™ 8730L

Polyolefin Elastomer

Introduction

Solumer™ 8730L is an **ethylene-octene copolymer** with ultra-high flowability produced via Nexlene™ technology. Solumer™ 8730L has excellent flow characteristics that provides ease in processing and is highly effective as an impact modifier or as a component in injection.

Applications

- Impact modification
- Industrial and consumer durable goods (injection)

Properties

		Typical Values	Unit	Test Method
Physical Properties	Density	0.868	g/cm ³	ASTM D792
	Melt index (2.16 kg @190°C)	30.0	g/10min	ASTM D1238
	Mooney viscosity (ML1+4 @ 121°C)	2	MU	ASTM D1646
Mechanical Properties¹	Tensile strength at break	32	kgf/cm ²	ASTM D638 ²
	Elongation at break	>1000	%	ASTM D638 ²
	Flexural modulus (1% secant)	110	kgf/cm ²	ASTM D790
	Tear strength (Type C)	30	kgf/cm ²	ASTM D624
	Hardness	Shore A (1 sec)	66	ASTM D2240
		Shore D (1 sec)	17	ASTM D2240
Thermal Properties	Melting temperature	61	°C	SK Method
	Glass transition temperature	-53	°C	SK Method

¹ Evaluated using compression molded sample

² Crosshead speed: 500 mm/min

Notes

These are **typical values** and are **not be construed as specifications**. The physical properties are highly dependent on the manufacturing conditions. So customers should confirm performances by their own tests.

For additional sales, order and technical assistance

Head office SK Global Chemical Co.,LTD
26 Jong-ro, Jongno-gu,
Seoul, Korea
TEL +82-2-2121-6757

TS&D SK innovation Global Technology
325 Expore,Yueseong-gu,
Daejeon, Korea
TEL +82-42-609-8623