

H7912

Description

Pellet type melt blown grade
Very high melt flow & very narrow MWD

Application

Diapers, Sanitary napkins, oil absorbent mats, wipes, wet tissues, masks, air filtration media and medicals

Properties	Method	Condition	Unit	H7912
Physical				
MFI	ASTM D1238	230°C, 2.16kg load	g/10min	1200
Density	ASTM D1505	Density-Gradient	g/cm ³	0.9

Note

The properties data in this table are typical values, and not guaranteed specification.
Typical resin property values are measured on a standard injection molded specimens.

Issued Date : 2022-03-14

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.