

BB150

Description

Application : Pharmaceutical bottle, Shrinkage film and Industrial packaging
 Additives : Non-Slip & Non-Antiblock agent

LUPURE BB150 can be used in "blow-fill and seal" machines for the production of ampoules and bottles.
 LUPURE BB150 has high transparent property.

Application

Pharmaceutical bottle

Properties	Method	Condition	Unit	BB150
Physical				
MFI	ASTM D1238	190°C, 2.16kg load	g/10min	0.8
Density	ASTM D1505	Density-Gradient	g/cm ³	0.922
Film Properties				
Tensile Strength at Break Point, MD	ASTM D882	500mm/min	kgf/cm ²	210
Tensile Strength at Break Point, TD	ASTM D882	500mm/min	kgf/cm ²	210
Elongation at Break Point, MD	ASTM D882	500mm/min	%	530
Elongation at Break Point, TD	ASTM D882	500mm/min	%	650
Dart Impact Strength	ASTM D1709	Method A	g	200
Haze(50µm)	ASTM D1003	50µm	%	7.1
Thermal				
Melting Temperature	LG Method	by DSC	°C	111
Vicat Softening Temperature	ASTM D1525	A50	°C	94

Note

The properties data in this table are typical values, and not guaranteed specification.
 Typical resin property values are measured on film specimens.

Issued Date : 2025-09-25

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.