

# XL8080NTS

## Description

Excellent electrical properties for medium voltage(below 35kV) power cable insulation  
 Very low level of contamination  
 Excellent surface finish and outstanding output rates over a broad range of conditions.

## Application

Wire & Cable Compound

Properties	Method	Condition	Unit	XL8080NTS
<b>Physical</b>				
Density(Base resin)	ISO1183	23°C	g/cm <sup>3</sup>	0.9215
<b>Mechanical</b>				
Tensile Strength	ISO 527	250mm/min	kgf/cm <sup>2</sup>	>200
Elongation	ISO 527	250mm/min	%	>500
Tensile Strength Retension after	ISO 60811-401	135°C, 168hrs	%	>90
Elongation Retension after	ISO 60811-401	135°C, 168hrs	%	>90
Hot Set Test(Elongation under Load)	IEC 60811-507	200°C, 0.2MPa	%	<175
Hot Set Test(Permanent Deformation)	IEC 60811-507	200°C, 0.2MPa	%	<15
<b>Electrical</b>				
Dielectric Constant	ASTM D1505	1MHz		2.3
Dissipation Factor	ASTM D1505	1MHz		0.0003
DC Volume Resistivity	ISO 60093	23°C	Ω·cm	>10 <sup>16</sup>
Dielectric Strength	IEC 60243		kV/mm	>22

## Note

The properties data in this table are typical values, and not guaranteed specification.  
 Typical resin property values are measured on a standard compression molded specimens.

Issued Date : 2023-07-25

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.