

LUTENE[®] XL8080UCS

XLPE

Applications

- Crosslinkable polyethylene compound for high and extra high voltage power cable insulation with rated voltage up to 230kV

Description

- LUTENE[®] XL8080UCS is a superior cleanliness version for high and extra high voltage power cable insulation and is designated as UC(Ultra-Clean) due to its extremely low level of contamination.

Specification

- LUTENE[®] XL8080UCS meets the property requirement of the following material specifications.
 - ① AEIC CS9
 - ② AEIC CS8
 - ③ KSC 3611
 - ④ ICEA S-94-649
 - ⑤ IEC 60502
 - ⑥ IEC 60840
 - ⑦ IEC 62067

Package

- Standard package : 600kg Carton Box, 1,000kg Carton Box
- Other package to customer's needs are also available.

Processing information

- LUTENE[®] XL8080UCS provides excellent surface finish and outstanding output rates over a broad range of extrusion conditions. When LUTENE[®] XL8080UCS is processed at melt temperature of 130 to 140°C, optimum results can be obtained.

For additional sales, order and technical assistance

Revised : 03/01/2022

Head office PO Division, LG Chem Ltd.
Yeoui-do P.O.Box 672, 21st floor LG Twin Tower,
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-6002/6003/6004

PO.TECH. Tech Center
Packaging TS 211, Hwangsae-ro, Osan-si, Gyeonggi-do, 18126,
Republic of Korea.
Tel. 82-31-5187-0215

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUTENE[®] XL8080UCS

XLPE

Typical properties

Characteristics	Test Method	Test Condition	Unit	Value
Physical				
Density, Base Resin	ISO 1183	23°C	g/cm ³	0.92
Mechanical				
Tensile Strength at Break	ISO 527	250mm/min	kg/cm ²	> 200
			Mpa	> 19.7
			psi	> 2,844
Elongation at Break	ISO 527	250mm/min	%	> 500
Tensile Strength Retension after	ISO 60811-401	135°C/168hrs	%	> 90
Elongation Retension after	ISO 60811-401	135°C/168hrs	%	> 90
Hot Set Test	IEC 60811-507	200°C, 0.2 Mpa	-	-
Elongation under Load			%	< 175
Permanent Deformation			%	< 15
Electrical				
Dielectric Constant	ASTM D150	1MHz	-	2.3
Dissipation factor	ASTM D150	1MHz		0.0003
DC Volume Resistivity	ISO 60093	23°C	Ω·cm	> 10 ¹⁶
Dielectric Strength	IEC 60243	-	kV/mm	> 22
Other				
Degree of Crosslinking	ASTM D2765A	-	%	> 80

* Measured on compression molded specimen

** NOTE : Values given above should only be used as a guide and should not be considered as a firm specification or guarantee.

Recommended to use within shelf life which is 12months from production date under the conditions that product is stored in unopened original packages, under dry and clean conditions at temperatures between 15 ~ 25°C.

Material shelf life is affected by the storage condition and extreme conditions influence the general material quality and performance.

For additional sales, order and technical assistance

Revised : 03/01/2022

Head office PO Division, LG Chem Ltd.
Yeoui-do P.O.Box 672, 21st floor LG Twin Tower,
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-6002/6003/6004

PO.TECH. Tech Center
Packaging TS 211, Hwangsae-ro, Osan-si, Gyeonggi-do, 18126,
Republic of Korea.
Tel. 82-31-5187-0215

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.